

# BOSS<sup>®</sup> PRODUCTS



# 125 Multi-Seal<sup>®</sup>

## ROOFING • GUTTERS • CONCRETE • CONSTRUCTION

### Colors:

#### Cartridge

- White - 12501
- Black - 12502
- Grey - 12503
- Limestone - 12507
- Alum/Grey - 12513
- Hunter Green - 12514
- Medium Bronze - 12515
- Off White - 12516
- Redwood Tan - 12517
- Stone - 12518
- Tan - 12519
- Special Bronze - 12520
- Brown - 12521
- Translucent - 12522

#### 1 Gallon pail

- Grey - 12573



- Plastic cartridge
- One year shelf life
- Applies the same in all seasons
- Bonds to wet, damp surfaces
- Long lasting, flexible adhesive
- Many colors available
- Paintable in under an hour\*
- Qualifies for LEED Credits
- VOC compliant
- Bonds to Kynar<sup>®</sup> 500

Kynar<sup>®</sup> 500 is a trademark of Arkema Inc.  
\*Translucent is not paintable

### THE IDEAL SEALANT/ADHESIVE FOR:

- Roofing
- Flashing
- Vents
- Gutters
- Tiles
- Wood
- Concrete
- Curbs
- Downspouts
- Pinhole repairs
- Masonry joints
- Exterior mastic
- Aluminum angle joints
- Asphalt Shingles
- Window & door perimeter joints
- Facade & metal clapping joints
- Concrete construction joints
- **MANY MORE...**

Visit Our Website for Other  
**BOSS<sup>®</sup> MADE TO WORK** Products  
[www.bossproducts.com](http://www.bossproducts.com)

- BOSS<sup>®</sup> 400** Colors Window & Siding Sealant
- BOSS<sup>®</sup> 399** Neutral Cure Silicone Glazing Sealant
- BOSS<sup>®</sup> 334** Genius Gun Minimal Expanding Foam
- BOSS<sup>®</sup> 334** Gun Grade Minimal Expanding Foam
- BOSS<sup>®</sup> 334** Straw Grade Minimal Expanding Foam



Call The **BOSS<sup>®</sup>** 800-928-BOSS  
Soudal

350 Ring Road • Elizabethtown • KY 42701  
(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412

# 125 Multi<sup>™</sup>Seal<sup>®</sup>

ROOFING • GUTTERS • CONCRETE • CONSTRUCTION

## TYPICAL PROPERTIES

	Colors	Translucent
<b>Uncured</b>		
Flow Sag or Slump .....	NIL .....	NIL .....
Tack Free Time .....	20 min .....	20 min .....
Extrusion Rate .....	400 g/min. ....	300 g/min. ....
<b>Cured – Physical</b>		
<b>7 Days at 77°F (25°C) and 50% RH (1/8" thickness)</b>		
Durometer Shore A Hardness .....	35 points .....	17 points .....
Specific Gravity .....	1.53 .....	1.01 .....
Tensile Strength .....	180 psi .....	180 .....
Elongation .....	350% .....	480% .....
Modulus .....	130 psi .....	50 psi .....
Shrinkage .....	NIL .....	NIL .....
Service Temperature .....	-40°F to 200°F	
Application Temperature .....	-35°F to 140°F	

Information on this data sheet is subject to change without notice and should not be used for writing specifications. For additional information on specific applications, contact Soudal.

### LIMITATIONS

- Do not use for structural glazing
- It is the sole responsibility of the user to test the adhesion to the substrate for suitability

### CAUTION

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Safety Data Sheet (SDS).

Call The **BOSS<sup>®</sup>** 800-928-BOSS  
Soudal

350 Ring Road • Elizabethtown • KY 42701  
(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412  
[www.bossproducts.com](http://www.bossproducts.com)

